

Priemyselná 720		Phone : +421 566880781					
072 22 Strážske, Slovenská Republika		Fax : +421 566880789					
<u>Type</u>		INTERGRATE® G.R.P. MOLDED <b>ECO-NFR SERIES</b> GRATING.					
Material		: Orthophtalic resin reinforced with continuous glass rovings.					
Color		: Steel grey RAL 9006.					
Density		: 1,5 – 2.					
Standard panel sizes		:					
Width [ mm ]	Length [ mm ]	Thickness [ mm ]	Mesh [ mm ]	Open area [ % ]	Weight [ kg / m <sup>2</sup> ]	Weight per panel [ kg ]	
1225	4580	13	51x51	78	3,9	21,9	
914	3048	25	38x38	70	12,2	34,0	
1219	2438	25	38x38	70	12,2	36,5	
1225	2980	30	38x38	70	14,1	51,5	
1000	1990	30	19x19	48	17,0	34,0	
1000	2980	30	19x19	48	17,0	50,7	
914	3048	38	38x38	70	18,3	51,0	
1219	2438	38	38x38	70	18,3	54,5	
1524	3048	38	38x38	70	18,3	85,0	
1000	2000	38	38x38	70	18,3	36,6	
1000	3000	38	38x38	70	18,3	54,9	
1000	4035	38	38x38	70	18,3	73,9	
1219	3658	38	38x38	70	18,3	81,4	
1645	2980	38	19x19	48	21,9	107,3	
Tolerances		: Length, width ± 1 mm		Thickness ± 2 mm		Warping < 10 mm / m <sup>*</sup> (* Not valid for 13 mm thickness).	
		: Weight ± 5%		Color deviation		Close to specified RAL-code.	
Load capacity		: Load deflection data based on walkway applications L/D = 100		( = 1 % ), consult Fiberstruct deflection table for specific load data.			
Glass / resin mix ratio		: Approx. 30 / 70 % by weight.					
Fire retardancy		: N.A.					
Operating temperature range		: - 40 °C / 60 °C.		For inside and outside applications (Ultra violet resistant).			
Slip resistancy		: R13 according to BGR 181 and DIN 51130.					
Others		: 1. Not electrical conductive.		2. Low thermal conductivity.		3. Voids, streaking and chip-outs according to Fiberstruct standards.	
Doc. No:	spec. by	: ing. L. Ondušková	checked by	: ir. P.J. Eijke			
01.00.04.00.	date	: 02.10.2007	date	: 02.10.2007			
Rev. : 5	signature	:	signature	:			