

Priemyselná 720 072 22 Strážske, Slovenská Republika				Phone : +421 566871311 Fax : +421 566871399		
<u>Type</u>		INTERGRATE® G.R.P. MOULDED <b>ECO-FR SERIES</b> GRATING.				
Material		: Orthophtalic fire retardant resin reinforced with continuous glass rovings.				
Color		: Grey RAL 7040.				
Density		: 1,5 – 2.				
Standard panel sizes		:				
Width [ mm ]	Length [ mm ]	Thickness [ mm ]	Mesh [ mm ]	Open area [ % ]	Weight [ kg / m <sup>2</sup> ]	Weight per panel [ kg ]
1225	4580	13	51x51	78	3,9	21,9
914	3048	25	38x38	70	12,2	34,0
1219	2438	25	38x38	70	12,2	36,5
1000	4037	30	38x38	70	14,1	56,9
1225	2980	30	38x38	70	14,1	51,5
1000	1990	30	19x19	48	17,0	34,0
1000	2980	30	19x19	48	17,0	50,7
1219	3658	30	19x19	48	17,0	75,8
914	3048	38	38x38	70	18,3	51,0
1219	2438	38	38x38	70	18,3	54,5
1524	3048	38	38x38	70	18,3	85,0
1524	4037	38	38x38	70	18,3	112,6
1000	3000	38	38x38	70	18,3	54,9
1000	4035	38	38x38	70	18,3	73,9
1219	3658	38	38x38	70	18,3	81,4
1645	2980	38	19x19	48	21,9	107,3
997	4047	38	19x19	48	21,9	88,4
1225	3665	38	19x19	48	21,9	98,3
1230	3665	51	51x51	78	23,4	105,4
Standardization		: Meets DIN24537-3				
Tolerances		: Length, width ± 1 mm Thickness ± 2 mm Warping < 10 mm / m* (* Not valid for 13 mm thickness). Weight ± 5% Color deviation Close to specified RAL-code.				
Load capacity		: Load deflection data based on walkway applications L/D = 100 (= 1 %), consult Fiberstruct deflection table for specific load data.				
Glass / resin mix ratio		: Approx. 30 / 70 % by weight.				
Fire retardancy		: 1. Self extinguishing. 2. According to ASTM E 84-05. Flame spread index (FSI): = 25 Smoke developed index (SDI): = 800 3. DNV Type approval				
Operating temperature range		: - 40 °C / 55 °C.				
Weathering		: For inside and outside applications (UV resistant).				
Slip resistancy		: R13 according to BGR 181 and DIN 51130.				
Approvals		: 1. DNV Type Approval 2. ABS Design Assessment				
Environmental		: Non-hazardous according to DNV MTPO360 version 2007 Part 1				
Others		: 1. Not electrical conductive. 2. Low thermal conductivity. 3. Voids, streaking and chip-outs according to Fiberstruct standards. 4. Meets REACH EU 1907/2006				

*PDS may be changed without prior notice. – This literature and the information it contains are based on data reasonably believed to be reliable. However, such factors as variations in environment, application or installation, changes in operating procedures, or extrapolation of data may cause different results. Fiberstruct makes no representation or warranty, expressed or implied, including warranties of merchantability or fitness for purpose, as to the accuracy, adequacy or completeness of the recommendations or information contained herein. Fiberstruct assumes no liability whatsoever in connection with this literature or the information or recommendations it contains.*